# NORBOND. 🖋



# A7300 SERIES

# Gray, Double-Sided, Acrylic Foam Tape

**Saint-Gobain® Norbond®** A7300 series is a gray, double-sided, coated acrylic foam tape with outstanding viscoelastic and adhesion properties. It offers ideal bonding performance for many interior and exterior industrial applications.Formulated for durable, long-lasting adhesion, A7300 exceeds industry standards for shear strength and bonding to high surface energy substrates, even at elevated temperatures.

The A7300 series viscoelastic core is specially designed to provide the following features:

- Great conformability and stretching
- Resistance to weathering degradation (UV and high temperature)
- Excellent performance in T-block and dynamic shear
- Outstanding static shear adhesion
- Durable adhesion at elevated temperature
- Shock and stress absorption

## **Available Sizes**

Standard thickness: 0.5mm (.020 in.), 0.8mm (.031 in.), 1.1mm (.043 in.)

Master roll size: 800mm (31.5 in.) x 33m (108 ft)

Special thickness and roll sizes also available.



# **APPLICATIONS**

- Signage/display bonding
- Bus, truck and trailer skin bonding
- Bus, truck and trailer roof bow bonding
- Replacement of permanent fastening systems (rivets, welds and liquid adhesives) used in general industrial applications



### **Norbond A7300 - Properties**

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

						Ì	Ĩ,	
Thickness	90° Peel Adhesion¹ (3-day dwell)				T-Block <sup>2</sup>	Dynamic Shear³	Static Shear⁴	
Without Liner	Glass	Aluminum	Stainless Steel	PMMA	Aluminum	Stainless Steel	Stainless Steel	Service Temperature
mm (in.)	N/cm (lb/in)	N/cm (lb/in)	N/cm (lb/in)	N/cm (lb/in)	N/cm <sup>2</sup> (lb/in <sup>2</sup> )	N/cm <sup>2</sup> (lb/in <sup>2</sup> )	7 days/1 kg	
0.5 (.020)	21 (12)	30 (17)	19 (11)	16 (9)	59 (86)	46 (67)	Pass and Exceeds	-35°C to 93°C (-30°F to 200°F)
0.8 (.031)	28 (16)	39 (22)	24 (14)	22 (13)	76 (110)	43 (62)	Pass and Exceeds	-35°C to 93°C (-30°F to 200°F)
1.1 (.043)	35 (20)	57 (33)	34 (20)	29 (17)	69 (100)	33 (48)	Pass and Exceeds	-35°C to 93°C (-30°F to 200°F)

<sup>1</sup> Based on ASTM D3330 <sup>2</sup> Based on ASTM D897 <sup>3</sup> Based on ASTM D1002 <sup>4</sup> Based on ASTM D3654

\_\_\_\_

#### **Options (subject to minimum order requirements)** Liner: A variety of substrate options (thickness, polymer, color, graphic printed) and release level options are

Liner: A variety of substrate options (thickness, polymer, color, graphic printed) and release level options are available upon request.

#### **Important Instructions**

- Because **Saint-Gobain** cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.
- Surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface.
- Apply a uniform pressure of 103 kPa (15 psi) to promote good contact between the material to be bonded and the tape. The application temperature should be between 16°C to 52°C (60°F and 125°F). It is not recommended to apply these tapes at temperatures below 16°C (60°F), as the adhesive does not flow in this condition and can result in poor bonding.
- The adhesion between the substrate and the tape increases with time, typically reaching final bond strength in 72 hours. Heating the product above 40°C (105°F) will accelerate the adhesion process.

#### **Shelf Life**

24 months after the date of manufacture when stored in original packaging at temperatures up to 21°C (70°F) and 50% relative humidity.



**Performance Plastics - Tape Solutions** 

North America | South America | Europe | Asia

For a full list of locations, please visit tapesolutions.saint-gobain.com/contact-us

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain Performance Plastics assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 24 months, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form #1004 | © Saint-Gobain April 2018 | Norbond and Saint-Gobain are trademarks of Saint-Gobain.