

V2800 SERIES

Black, Closed-Cell, Polyurethane Foam Tape

Saint-Gobain® Norbond® V2800 series bonding tapes combine a black polyurethane foam substrate with a high-performance, pressure-sensitive acrylic adhesive on both sides. The foam substrate allows energy and stress in the joint to be dissipated over the entire bond. **Norbond** V2800 is an ideal choice for severe exterior bonding applications. The product is durable in all weather conditions and provides resistance against UV light, extreme temperatures, fungi, oxidation and ozone.

The V2800 series is specially designed to provide the following features:

- Stress distribution reduces pressure points, thereby minimizing distortion
- High-performance, durable acrylic adhesive provides a strong, long-lasting bond
- Conformable, closed-cell polyurethane foam has excellent environmental resistance
- Prevents corrosion of dissimilar materials by eliminating the contact between them
- Standard polyethylene liner excels in automated production

Available Sizes

Standard thickness: .030, .045, .062, .090 and .120 in.

Master roll size: 56 in. (1422 mm) width. Slit rolls also available. Standard roll length varies with thickness.

Nonstandard roll length available on special order.



APPLICATIONS

- Window muntin bars
- Emblems and ornamentation
- Trailer roof bows
- Panel stiffeners
- Signs and nameplates
- Weatherstripping
- Body side molding
- Composite panels

Norbond V2800 Series – Properties

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Test Method	Value or Rating
Density: lbs/ft ³ (kg/m ³)	ASTM D-1667	30 (480)
Peel Adhesion oz/in (N/m) 180° Peel 15-min. dwell	PSTC-3	108 (1,181)
Dynamic Shear Adhesion:psi (kPa), 72 hr. dwell stainless steel to paint	NTP-5	120 (827)
Dynamic Tensile Adhesion: psi (kPa) 24 hr. dwell aluminum to paint	NTP-11	100 (689)
Tensile Strength of Foam: psi (kPa)	ASTM D-412 DIE C	130 (896)
Elongation of Foam: %	ASTM D-412 DIE C	275
Water Absorption: % by weight	NTP-36	5

NTP- Norton Test Procedure

Options (subject to minimum order requirements)

Liner: Powder-blue polyethylene liner is standard. Other liners may be available with minimum order requirement.

Important Instructions

- Because **Saint-Gobain** cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.
- Surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface.
- Apply a uniform pressure of 15 psi (103 kPa) to promote good contact between the material to be bonded and the tape. The application temperature should be between 60°F and 125°F (16°C to 52°C). It is not recommended to apply these tapes at temperatures below 60°F (16°C), as the adhesive does not flow in this condition and can result in poor bonding.
- Recommended Service Temperature is between -40°F to 200°F (-40°C to 93°C).
- The adhesion between the substrate and the tape increases with time, typically reaching final bond strength in 72 hours. Heating the product above 105°F (40°C) will accelerate the adhesion process.

Shelf Life

12 months after the date of sale when stored in original packaging at temperatures up to 70°F (21°C) and 50% relative humidity.

Norbond V2800 – Standard Roll Sizes

Product No.	Thickness in. (mm)	Length ft. (m)
V2830	.030 (.8)	200 (61)
V2845	.45 (1.2)	200 (61)
V2862	.062 (1.5)	200 (61)
V2890	.090 (2.3)	150 (45)
V28120	.120 (3.0)	50 (15)

3" I.D. cardboard cores standard



Need more adhesion? Stick with Saint-Gobain Norbond Adhesion Promoters.

Norbond adhesion promoters are designed to work in conjunction with acrylic, pressure-sensitive adhesive systems (such as those used on **Norbond** tapes).

Norbond improves bonding on substrates that resist adhesion. It can be used to develop an immediate quick-stick and generally improves pressure-sensitive acrylic adhesive systems. This enhances adhesion to irregular and curved surfaces. Various formulations are available for specific substrates.

SAINT-GOBAIN

Performance Plastics - Tape Solutions

North America | South America | Europe | Asia

For a full list of locations, please visit tapesolutions.saint-gobain.com/contact-us

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain Performance Plastics assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 6 months, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. **SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.**

Form #1013 | © Saint-Gobain December 2017 | **Norbond** and **Saint-Gobain** are trademarks of Saint-Gobain.