



PRODUCT SPECIFICATIONS

Z1845DC POLYETHER POLYURETHANE FOAM

Tentative Specification

PHYSICAL PROPERTIES

TEST VALUES

	U.S. STANDARD		METRIC	
	MINIMUM	AVERAGE	MINIMUM	AVERAGE
Density	1.80 ± 10 % lbs./ft. ³		28.8 ± 10 % kg/M ³	
Tensile Strength	12.0 psi	18.0 psi	83 kPa	124 kPa
Elongation	80%	120%	80%	120%
Indentation Force Deflection				
25% Deflection	40 lbs./50 in. ²	55 lbs./50 in. ²	178 N/323cm ²	245 N/323cm ²
65% Deflection	70 lbs./50 in. ²	100 lbs./50 in. ²	311 N/323cm ²	445 N/323cm ²
Retention of Tensile Strength after 3 hours, 105°C, steam autoclave			Min. 70%	
Air Flow	5.00 ft ³ / 4 in ² / min		54.85 m ³ / m ² / min	

Features:

- This product contains additives to retard microbial growth and degradation.
- Recommended for outdoor seating applications
- Minimum Airflow (ASTM D3574, Test G) 5.00 SCFM air
- Cell size: 30 to 40 cells/inch

* Test Methods : ASTM-D3574-[latest revision]. Standard Methods of Testing Flexible Cellular Materials - Slab, Bonded, and Molded Urethane Foam.

NOTE: This specification is for flat foam only.

ERROR: syntaxerror
OFFENDING COMMAND: --nostringval--

STACK:

/Title
()
/Subject
(D:20090603132749-04'00')
/ModDate
()
/Keywords
(PDFCreator Version 0.9.5)
/Creator
(D:20090603132749-04'00')
/CreationDate
(rodneybl)
/Author
-mark-